



12500 TI Boulevard, MS 8640, Dallas, Texas 75243

PCN# 20260331002.1
Qualifying a Design change, Fab process and FMX as an
additional Assembly site option for select devices
Change Notification / Sample Request

Date: March 31, 2026

Dear Customer:

This is an announcement of a change to a device that is currently offered by Texas Instruments. The details of this change are on the following pages.

Texas Instruments requires acknowledgement of receipt of this notification within 60 days of the date of this notice. Lack of acknowledgement of this notice within 60 days constitutes acceptance and approval of this change. If samples or additional data are required, requests must be received within 60 days of this notification.

The changes discussed within this PCN will not take effect any earlier than the proposed first ship date on Page 3 of this notification, unless customer agreement has been reached on an earlier implementation of the change.

This notice does not change the end-of-life status of any product. Should product affected be on a previously issued product withdrawal/discontinuance notice, this notification does not extend the life of that product or change the life time buy offering/discontinuance plan.

For questions regarding this notice or to provide acknowledgement of this PCN, you may contact your local Field Sales Representative or the change management team.

For sample requests or sample related questions, contact your local Field Sales Representative.

TI values customer engagement and feedback related to TI changes. Customers should contact TI if there are questions or concerns regarding a change notification.

Sincerely,

Change Management Team
SC Business Services

20260331002.1
Attachment: 1

Products Affected:

The devices listed on this page are a subset of the complete list of affected devices. According to our records, you have recently purchased these devices. The corresponding customer part number is also listed, if available.

DEVICE	CUSTOMER PART NUMBER
CD74HC04E	
CD74HC14E	
SN74HC7001DR	
SN74HC08NSR	
CD74HC132E	
CD74HC00M96	
SN74HC08N	
SN74HC00DR	
SN74HC14PWR	
SN74HC02DR	
SN74HC02PWR	
SN74HC14N	
SN74HC04DR	
SN74HC00DRG4	
SN74HC14DBR	
SN74HC10DR	
SN74HC00PWR	
CD74HC02M96	
SN74HC04DR	
SN74HC08DR	
SN74HC132N	
SN74HC7001DR	
SN74HC00N	
CD74HC08M96	
SN74HC14DR	
CD74HC132E	
SN74HC08DR	
SN74HC08DRG4	
SN74HC132N	
CD74HC02M96	
SN74HC02NSR	
CD74HC04M96	
SN74HC08N	
SN74HC05PWR	
SN74HC14NSR	
SN74HC10N	
CD74HC14M96	
SN74HC04N	
SN74HC14ANSR	
SN74HC14N	
CD74HC14M96	
SN74HC14DRG4	
SN74HC02N	
SN74HC02DRG4	
SN74HC02PWR	
CD74HC02E	
CD74HC02E	
SN74HC04N	
CD74HC10M96	

SN74HC00DR	
SN74HC14DR	
SN74HC10DR	
SN74HC14PWR	
SN74HC08PWR	
SN74HC04DRG4	
SN74HC05DR	
CD74HC00E	
SN74HC132DR	
CD74HC132M96	
SN74HC14DRG4	
CD74HC4075M96	
SN74HC04PWR	
CD74HC00M96	
CD74HC08M96	
CD74HC14E	
CD74HC00E	
SN74HC00N	

Technical details of this Product Change follow on the next page(s).

PCN Number:	20260331002.1		PCN Date:	March 31, 2026																									
Title:	Qualifying a Design change, Fab process and FMX as an additional Assembly site option for select devices																												
Customer Contact:	Change Management team		Dept:	Quality Services																									
Proposed 1st Ship Date:	June 29, 2026		Sample requests accepted until:	May 30, 2026*																									
*Sample requests received after May 30, 2026 will not be supported.																													
Change Type:																													
☒	Assembly Site	☒	Design	☐	Wafer Bump Material																								
☐	Assembly Process	☐	Data Sheet	☐	Wafer Bump Process																								
☐	Assembly Materials	☐	Part number change	☐	Wafer Fab Site																								
☐	Mechanical Specification	☐	Test Site	☐	Wafer Fab Material																								
☒	Packing/Shipping/Labeling	☐	Test Process	☒	Wafer Fab Process																								
PCN Details																													
Description of Change:																													
Texas Instruments is pleased to announce a die design and fab process update for improved manufacturing efficiency & Qualify FMX as additional Assembly site options for the select devices listed below. <table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th colspan="3">Current</th> <th colspan="3">Proposed</th> </tr> <tr> <th>Fab Site</th> <th>Process</th> <th>Wafer Diameter</th> <th>Fab site</th> <th>Process</th> <th>Wafer Diameter</th> </tr> </thead> <tbody> <tr> <td>RFAB</td> <td>LBC9</td> <td>300mm</td> <td>RFAB</td> <td>LBC9 PLV</td> <td>300mm</td> </tr> </tbody> </table> The die revision was also changed as a result of the process change. Group 1 device (Design only): Device remains at existing Assembly site Group 2 device (Design, Assembly site) <table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th></th> <th>Current site</th> <th>Additional Site</th> </tr> </thead> <tbody> <tr> <td>Assembly site</td> <td>MLA</td> <td>FMX</td> </tr> </tbody> </table> *No material differences between sites Qual details are provided in the Qual Data Section.						Current			Proposed			Fab Site	Process	Wafer Diameter	Fab site	Process	Wafer Diameter	RFAB	LBC9	300mm	RFAB	LBC9 PLV	300mm		Current site	Additional Site	Assembly site	MLA	FMX
Current			Proposed																										
Fab Site	Process	Wafer Diameter	Fab site	Process	Wafer Diameter																								
RFAB	LBC9	300mm	RFAB	LBC9 PLV	300mm																								
	Current site	Additional Site																											
Assembly site	MLA	FMX																											
Reason for Change:																													
Improve Manufacturing Efficiency																													
Anticipated impact on Fit, Form, Function, Quality or Reliability (positive / negative):																													
Review the SDP for full evaluation of the change based on the customer use case.																													
Impact on Environmental Ratings																													
Checked boxes indicate the status of environmental ratings following implementation of this change. If below boxes are checked, there are no changes to the associated environmental ratings.																													

RoHS		REACH		Green Status		IEC 62474			
☒ No Change	☒ No Change	☒ No Change	☒ No Change	☒ No Change	☒ No Change	☒ No Change	☒ No Change		
Changes to product identification resulting from this PCN:									
Die Rev: Current New Die Rev [2P] Die Rev [2P] <table border="1" style="width: 100%;"> <tr> <td style="text-align: center; color: blue;">B</td> <td style="text-align: center; color: blue;">A</td> </tr> </table>								B	A
B	A								
Assembly Site Information:									
Assembly Site	Assembly Site Origin (22L)	Assembly Country Code (23L)	Assembly City						
TI Malaysia	MLA	MYS	Kuala Lumpur						
TI Mexico	MEX	MEX	Aguascalientes						
Sample product shipping label (not actual product label)									
 TEXAS INSTRUMENTS MADE IN: Malaysia 2DC: 2Q: MSL 2 /260C/1 YEAR SEAL DT MSL 1 /235C/UNLIM 03/29/04 OPT: ITEM: 39 LBL: 5A (L)T0:1750  (1P) SN74LS07NSR (Q) 2000 (D) 0336 (31T) LOT: 3959047MLA (4W) TKY (1T) 7523483SI2 (P) (2P) REV: (V) 0033317 (20L) CS0: SHE (21L) CCO:USA (22L) AS0: MLA (23L) ACO: MYS									
Group 1 Product Affected: (Design only)									

CD74HC00E	SN74HC02DRG4	SN74HC08NSR
CD74HC00EE4	SN74HC02N	SN74HC08PWR
CD74HC02E	SN74HC02NE4	SN74HC08PWRG4
CD74HC04E	SN74HC02NSR	SN74HC10N
CD74HC04M96	SN74HC02NSRG4	SN74HC10NE4
CD74HC08PWRG4	SN74HC02PWR	SN74HC10NSR
CD74HC132E	SN74HC02PWRG4	SN74HC10NSRG4
CD74HC132EE4	SN74HC04DR	SN74HC10PWRG4
CD74HC14E	SN74HC04DRG4	SN74HC132DR
CD74HC14EE4	SN74HC04N	SN74HC132N
CD74HC14M96	SN74HC04NE4	SN74HC132NE4
CD74HC14PWRG4	SN74HC04NSR	SN74HC132NSR
CD74HC4075NSR	SN74HC04NSRG4	SN74HC132NSRG4
CD74HC4075PWRG4	SN74HC04PWR	SN74HC132PWR1G4
SN74HC00ANSR	SN74HC04PWRG4	SN74HC14ANSR
SN74HC00APWR	SN74HC05DRG4	SN74HC14DBR
SN74HC00DR	SN74HC05NSR	SN74HC14DR
SN74HC00DRG4	SN74HC05NSRE4	SN74HC14DRG4
SN74HC00N	SN74HC05PWR	SN74HC14N
SN74HC00NE4	SN74HC05PWRG4	SN74HC14NE4
SN74HC00NSR	SN74HC08ANSR	SN74HC14NSR
SN74HC00PWR	SN74HC08DR	SN74HC14NSRE4
SN74HC00PWRG4	SN74HC08DRG4	SN74HC14PWR
SN74HC02ANSR	SN74HC08N	SN74HC14PWRG4
SN74HC02DR	SN74HC08NE4	

Group 2 Product Affected: (Design, Assembly site)

CD74HC00M96	CD74HC10M96	SN74HC10DR
CD74HC00M96G4	CD74HC132M96	SN74HC10DRG4
CD74HC02M96	CD74HC132M96G4	SN74HC132DR1G4
CD74HC02M961G4	CD74HC14M961G4	SN74HC7001DR
CD74HC04M96G4	CD74HC4075M96	SN74HC7001DRG4
CD74HC08M96	CD74HC4075M96G4	
CD74HC08M961G4	SN74HC05DR	

Group 1 Qualification Report

BD123 14 PIN N

Approve Date 13-MARCH -2026

Qualification Results

Data Displayed as: Number of lots / Total sample size / Total failed

Type	#	Test Name	Condition	Duration	Qual Device: SN74HC14N	QBS Process Reference: SN74HCS74QPWRQ1	QBS Package Reference: SN74HC00N	QBS Package Reference: SN74HC04N	QBS Package Reference: SN74HC164N	QBS Package Reference: NE556N	QBS Product Reference: SN74HC14QPWRQ1
HAST	A2	Biased HAST	130C/85%RH	96 Hours	-	3/231/0	1/77/0	1/77/0	1/77/0	-	1/77/0
UHA	A3	Autoclave	121C/15psig	96 Hours	-	3/231/0	-	-	-	-	-
UHA	A3	Unbiased HAST	130C/85%RH	96 Hours	-	-	-	-	-	1/77/0	1/77/0
TC	A4	Temperature Cycle	-65C/150C	500 Cycles	-	3/231/0	1/77/0	-	-	1/77/0	1/77/0
HTSL	A6	High Temperature Storage Life	150C	1000 Hours	-	3/135/0	-	-	-	-	1/45/0
HTSL	A6	High Temperature Storage Life	170C	420 Hours	-	-	-	-	-	1/77/0	-
HTOL	B1	Life Test	125C	1000 Hours	-	3/231/0	-	-	-	-	1/77/0
ELFR	B2	Early Life Failure Rate	125C	48 Hours	-	3/2400/0	-	-	-	-	-
SD	C3	PB Solderability	Precondition w.155C Dry Bake (4 hrs +/- 15 minutes)	-	-	1/15/0	-	-	-	-	-
SD	C3	PB-Free Solderability	Precondition w.155C Dry Bake (4 hrs +/- 15 minutes)	-	-	1/15/0	-	-	-	-	-
SD	C3	PB-Free Solderability	Precondition w.155C Dry Bake (4 hrs +/- 15 minutes); PB-Free Solder;	-	1/22/0	-	-	-	-	-	-
PD	C4	Physical Dimensions	Cpk>1.67	-	-	3/30/0	-	-	-	-	1/10/0
ESD	E2	ESD CDM	-	2000 Volts	-	-	1/3/0	-	-	-	-
ESD	E2	ESD CDM	-	250 Volts	1/3/0	-	-	-	-	1/3/0	-
ESD	E2	ESD CDM	-	500 Volts	1/3/0	1/3/0	-	-	-	-	1/3/0
ESD	E2	ESD CDM	-	750 Volts	1/3/0	-	-	-	-	-	1/3/0
ESD	E2	ESD HBM	-	1000 Volts	1/3/0	-	-	-	-	1/3/0	-
ESD	E2	ESD HBM	-	2000 Volts	-	1/3/0	-	-	-	-	1/3/0
LU	E4	Latch-Up	Per JESD78	-	1/3/0	1/6/0	-	-	-	1/3/0	1/3/0
CHAR	E5	Electrical Characterization	Per Datasheet Parameters	-	1/30/0	-	-	-	-	1/30/0	-
CHAR	E5	Electrical Distributions	Cpk>1.67 Room, hot, and cold	-	-	3/90/0	-	-	-	-	3/90/0

QBS: Qual By Similarity, also known as Generic Data

Qual Device SN74HC14N is qualified at NOT CLASSIFIED 260C

Preconditioning was performed for Autoclave, Unbiased HAST, THB/Biased HAST, Temperature Cycle, Thermal Shock, and HTSL, as applicable

The following are equivalent HTOL options based on an activation energy of 0.7eV : 125C/1k Hours, 140C/480 Hours, 150C/300 Hours, and 155C/240 Hours

The following are equivalent HTSL options based on an activation energy of 0.7eV : 150C/1k Hours, and 170C/420 Hours

The following are equivalent Temp Cycle options per JESD47 : -55C/125C/700 Cycles and -65C/150C/500 Cycles

Quality and Environmental data is available at TI's external Web site: <http://www.ti.com/>

TI Qualification ID: R-CHG-2509-111

Qualification Report
BD123 14 PIN D
Approve Date 17-March-2026

Qualification Results

Data Displayed as: Number of lots / Total sample size / Total failed

Type	#	Test Name	Condition	Duration	Qual Device: SN74HC08DR	Qual Device: SN74HC14DR	Qual Device: SN74HCS14DR	Qual Device: SN74HCS266DR	QBS Process Reference: SN74HCS14QPMRQ1	QBS Package Reference: SN74LVCT11ADRQ1	QBS Package Reference: SN74LVCT32ADRQ1	QBS Package Reference: SN74LVCT44ADRQ1	QBS Product Reference: SN74HC08DR	QBS Product Reference: SN74HC14PWR	QBS Product Reference: SN74HCS14PWR	QBS Product Reference: SN74HCS266PWR
HAST	A2	Biased HAST	130C/85%RH	96 Hours	-	-	-	-	3/231/0	1/77/0	1/77/0	1/77/0	-	-	-	-
UHAST	A3	Autoclave	121C/15psig	96 Hours	-	-	-	-	3/231/0	1/77/0	1/77/0	1/77/0	-	-	-	-
TC	A4	Temperature Cycle	-55C/150C	500 Cycles	-	-	-	-	3/231/0	1/77/0	1/77/0	1/77/0	-	-	-	-
HTSL	A6	High Temperature Storage Life	150C	1000 Hours	-	-	-	-	3/135/0	-	-	-	-	-	-	-
HTSL	A6	High Temperature Storage Life	175C	500 Hours	-	-	-	-	-	1/45/0	1/45/0	1/45/0	-	-	-	-
HTOL	B1	Life Test	125C	1000 Hours	-	-	-	-	3/231/0	-	-	-	-	-	-	-
HTOL	B1	Life Test	150C	300 Hours	-	-	-	-	-	1/77/0	-	-	-	-	-	-
ELFR	B2	Early Life Failure Rate	125C	48 Hours	-	-	-	-	3/2400/0	-	-	-	-	-	-	-
SD	C3	PB Solderability	Precondition w/155C Dry Bake (4 hrs +/- 15 minutes)	-	-	-	-	-	1/15/0	-	-	-	-	-	-	-
SD	C3	PB-Free Solderability	Precondition w/155C Dry Bake (4 hrs +/- 15 minutes)	-	-	-	-	-	1/15/0	1/15/0	-	-	-	-	-	-
PD	C4	Physical Dimensions	Cpk>1.67	-	-	-	-	-	3/30/0	1/10/0	1/10/0	1/10/0	-	-	-	-
ESD	E2	ESD CDM	-	250 Volts	1/3/0	1/3/0	1/3/0	1/3/0	-	-	-	-	-	1/3/0	1/3/0	1/3/0
ESD	E2	ESD CDM	-	500 Volts	-	-	-	-	1/3/0	1/3/0	1/3/0	1/3/0	-	-	-	-
ESD	E2	ESD HBM	-	1000 Volts	-	-	-	1/3/0	-	-	-	-	-	1/3/0	1/3/0	1/3/0
ESD	E2	ESD HBM	-	2000 Volts	-	-	-	-	1/3/0	1/3/0	-	-	-	-	-	-
LU	E4	Latch-Up	Per JESD78	-	-	-	-	1/3/0	1/6/0	1/3/0	-	-	-	1/3/0	1/3/0	1/3/0
CHAR	E5	Electrical Characterization	Per DataSheet Parameters	-	1/30/0	1/30/0	1/30/0	1/30/0	-	-	-	-	1/30	1/30/0	1/30/0	1/30/0
CHAR	E5	Electrical Disturbances	Cpk>1.67 Room, hot, and cold	-	-	-	-	-	3/60/0	2/60/0	1/30/0	1/30/0	-	-	-	-

QBS: Qual By Similarity, also known as Generic Data

Qual Device SN74HC08DR is qualified at MSL1 260C

Qual Device SN74HC14DR is qualified at MSL1 260C

Qual Device SN74HCS14DR is qualified at MSL1 260C

Qual Device SN74HCS266DR is qualified at MSL1 260C

Preconditioning was performed for Autoclave, Unbiased HAST, THB/Biased HAST, Temperature Cycle, Thermal Shock, and HTSL, as applicable

The following are equivalent HTOL options based on an activation energy of 0.7eV : 125C/1k Hours, 140C/480 Hours, 150C/300 Hours, and 155C/240 Hours

The following are equivalent HTSL options based on an activation energy of 0.7eV : 150C/1k Hours, and 170C/420 Hours

The following are equivalent Temp Cycle options per JESD47 : -55C/125C/700 Cycles and -65C/150C/500 Cycles

Quality and Environmental data is available at TI's external Web site: <http://www.ti.com/>

TI Qualification ID: R-CHG-2601-070

Qualification Report
BD123 14 PIN NS
Approve Date 13-March-2026

Qualification Results

Data Displayed as: Number of lots / Total sample size / Total failed

Type	#	Test Name	Condition	Duration	Qual Device: SN74HC14NSR	QBS Process Reference: SN74HCS74QFWRQ1	QBS Package Reference: SN74LVC8T245NSR	QBS Package Reference: TXS0108EQDGSQRQ1	QBS Package Reference: SN74AC3G99DGSQRQ1	QBS Package Reference: TPLD1201DGSQRQ1	QBS Product Reference: SN74HC14QFWRQ1
HAST	A2	Biased HAST	130C/85%RH	96 Hours	-	3/231/0	-	1/77/0	1/77/0	1/77/0	1/77/0
UHA	A3	Autoclave	121C/15psig	96 Hours	-	3/231/0	-	-	-	-	-
UHA	A3	Unbiased HAST	130C/85%RH	96 Hours	-	-	-	1/77/0	1/77/0	1/77/0	1/77/0
TC	A4	Temperature Cycle	-65C/150C	500 Cycles	-	3/231/0	3/231/0	3/231/0	1/77/0	1/77/0	1/77/0
HTSL	A6	High Temperature Storage Life	150C	1000 Hours	-	3/135/0	3/231/0	1/45/0	1/45/0	-	1/45/0
HTSL	A6	High Temperature Storage Life	175C	500 Hours	-	-	-	-	-	1/45/0	-
HTOL	B1	Life Test	125C	1000 Hours	-	3/231/0	-	1/77/0	-	-	1/77/0
HTOL	B1	Life Test	150C	300 Hours	-	-	-	-	-	3/231/0	-
ELFR	B2	Early Life Failure Rate	125C	48 Hours	-	3/2400/0	-	-	-	-	-
SD	C3	PB Solderability	Precondition w.155C Dry Bake (4 hrs +/- 15 minutes)	-	-	1/15/0	-	-	-	-	-
SD	C3	PB-Free Solderability	Precondition w.155C Dry Bake (4 hrs +/- 15 minutes)	-	-	1/15/0	-	-	-	-	-
SD	C3	PB-Free Solderability	Precondition w.155C Dry Bake (4 hrs +/- 15 minutes); PB-Free Solder;	-	1/22/0	-	-	-	-	-	-
PD	C4	Physical Dimensions	Cpk>1.67	-	-	3/30/0	-	1/10/0	1/10/0	1/10/0	1/10/0
ESD	E2	ESD CDM	-	250 Volts	1/3/0	-	-	-	-	-	-
ESD	E2	ESD CDM	-	500 Volts	1/3/0	1/3/0	-	1/3/0	1/3/0	1/3/0	1/3/0
ESD	E2	ESD CDM	-	750 Volts	1/3/0	-	-	-	-	-	1/3/0
ESD	E2	ESD HBM	-	2000 Volts	1/3/0	1/3/0	-	-	1/3/0	1/3/0	1/3/0
LU	E4	Latch-Up	Per JESD78	-	1/3/0	1/6/0	-	-	1/3/0	1/3/0	1/3/0
CHAR	E5	Electrical Characterization	Per Datasheet Parameters	-	1/30/0	-	-	-	-	-	-
CHAR	E5	Electrical Distributions	Cpk>1.67 Room, hot, and cold	-	-	3/90/0	-	1/30/0	1/30/0	3/90/0	3/90/0

QBS: Qual By Similarity, also known as Generic Data

Qual Device SN74HC14NSR is qualified at MSL1 260C

Preconditioning was performed for Autoclave, Unbiased HAST, THB/Biased HAST, Temperature Cycle, Thermal Shock, and HTSL, as applicable

The following are equivalent HTOL options based on an activation energy of 0.7eV : 125C/1k Hours, 140C/480 Hours, 150C/300 Hours, and 155C/240 Hours

The following are equivalent HTSL options based on an activation energy of 0.7eV : 150C/1k Hours, and 170C/420 Hours

The following are equivalent Temp Cycle options per JESD47 : -55C/125C/700 Cycles and -65C/150C/500 Cycles

Quality and Environmental data is available at TI's external Web site: <http://www.ti.com/>

TI Qualification ID: R-CHG-2509-112

Qualification Report BD123 14 PIN DB Approve Date 13-March-2026

Qualification Results

Data Displayed as: Number of lots / Total sample size / Total failed

Type	#	Test Name	Condition	Duration	Qual Device: SN74HC14DBR	QBS Process Reference: SN74HCS74QPWRQ1	QBS Package Reference: TLC320AD77CDBR	QBS Package Reference: PCM1794AQDBRQ1	QBS Product Reference: SN74HC14NSR	QBS Product Reference: SN74HC14QPWRQ1
HAST	A2	Biased HAST	130C/85%RH	96 Hours	-	3/231/0	-	3/231/0	-	1/77/0
UHAST	A3	Autoclave	121C/15psig	96 Hours	-	3/231/0	-	3/231/0	-	-
UHAST	A3	Unbiased HAST	130C/85%RH	96 Hours	-	-	3/231/0	-	-	1/77/0
TC	A4	Temperature Cycle	-65C/150C	500 Cycles	-	3/231/0	3/231/0	3/231/0	-	1/77/0
HTSL	A6	High Temperature Storage Life	150C	1000 Hours	-	3/135/0	3/231/0	-	-	1/45/0
HTSL	A6	High Temperature Storage Life	175C	500 Hours	-	-	-	1/45/0	-	-
HTOL	B1	Life Test	125C	1000 Hours	-	3/231/0	-	3/231/0	-	1/77/0
ELFR	B2	Early Life Failure Rate	125C	48 Hours	-	3/2400/0	-	3/2400/0	-	-
SD	C3	PB Solderability	Precondition w.155C Dry Bake (4 hrs +/- 15 minutes)	-	-	1/15/0	-	-	-	-
SD	C3	PB-Free Solderability	Precondition w.155C Dry Bake (4 hrs +/- 15 minutes)	-	-	1/15/0	-	-	-	-
SD	C3	PB-Free Solderability	Precondition w.155C Dry Bake (4 hrs +/- 15 minutes); PB- Free Solder;	-	1/22/0	-	-	-	1/22/0	-
PD	C4	Physical Dimensions	Cpk>1.67	-	-	3/30/0	-	3/30/0	-	1/10/0
ESD	E2	ESD CDM	-	250 Volts	1/3/0	-	-	-	1/3/0	-
ESD	E2	ESD CDM	-	500 Volts	1/3/0	1/3/0	-	1/3/0	-	1/3/0
ESD	E2	ESD CDM	-	750 Volts	1/3/0	-	-	-	-	1/3/0
ESD	E2	ESD HBM	-	2000 Volts	1/3/0	1/3/0	-	1/3/0	-	1/3/0
LU	E4	Latch-Up	Per JESD78	-	1/3/0	1/6/0	-	1/6/0	-	1/3/0
CHAR	E5	Electrical Characterization	Per Datasheet Parameters	-	1/30/0	-	-	-	1/30/0	-
CHAR	E5	Electrical Distributions	Cpk>1.67 Room, hot, and cold	-	-	3/90/0	-	3/90/0	-	3/90/0

QBS: Qual By Similarity, also known as Generic Data

Qual Device SN74HC14DBR is qualified at MSL1 260C

Preconditioning was performed for Autoclave, Unbiased HAST, THB/Biased HAST, Temperature Cycle, Thermal Shock, and HTSL, as applicable

The following are equivalent HTOL options based on an activation energy of 0.7eV : 125C/1k Hours, 140C/480 Hours, 150C/300 Hours, and 155C/240 Hours

The following are equivalent HTSL options based on an activation energy of 0.7eV : 150C/1k Hours, and 170C/420 Hours

The following are equivalent Temp Cycle options per JESD47 : -55C/125C/700 Cycles and -65C/150C/500 Cycles

Quality and Environmental data is available at TI's external Web site: <http://www.ti.com/>

TI Qualification ID: R-CHG-2509-109

Qualification Report BD123 14 PIN PW Approve Date 13-March-2026

Qualification Results

Data Displayed as: Number of lots / Total sample size / Total failed

Type	#	Test Name	Condition	Duration	Qual Device: SN74HCS11PWR	Qual Device: SN74HC14PWR	Qual Device: SN74HCS14PWR	Qual Device: SN74HCS4075PWR	QBS Package, Process Reference: SN74HCS74QPWRQ1	QBS Product Reference: SN74HC14QPWRQ1
HAST	A2	Biased HAST	130C/85%RH	96 Hours	-	-	-	-	3/231/0	1/77/0
UHA	A3	Autoclave	121C/15psig	96 Hours	-	-	-	-	3/231/0	-
UHA	A3	Unbiased HAST	130C/85%RH	96 Hours	-	-	-	-	-	1/77/0
TC	A4	Temperature Cycle	-65C/150C	500 Cycles	-	-	-	-	3/231/0	1/77/0
HTSL	A6	High Temperature Storage Life	150C	1000 Hours	-	-	-	-	3/135/0	1/45/0
HTOL	B1	Life Test	125C	1000 Hours	-	-	-	-	3/231/0	1/77/0
ELFR	B2	Early Life Failure Rate	125C	48 Hours	-	-	-	-	3/2400/0	-
SD	C3	PB Solderability	Precondition w.155C Dry Bake (4 hrs +/- 15 minutes)	-	-	-	-	-	1/15/0	-
SD	C3	PB-Free Solderability	Precondition w.155C Dry Bake (4 hrs +/- 15 minutes)	-	-	-	-	-	1/15/0	-
PD	C4	Physical Dimensions	Cpk>1.67	-	-	-	-	-	3/30/0	1/10/0
ESD	E2	ESD CDM	-	250 Volts	1/3/0	1/3/0	1/3/0	1/3/0	-	-
ESD	E2	ESD CDM	-	500 Volts	-	-	-	-	1/3/0	1/3/0
ESD	E2	ESD CDM	-	750 Volts	-	-	-	-	-	1/3/0
ESD	E2	ESD HBM	-	1000 Volts	1/3/0	1/3/0	1/3/0	1/3/0	-	-
ESD	E2	ESD HBM	-	2000 Volts	-	-	-	-	1/3/0	1/3/0
LU	E4	Latch-Up	Per JESD78	-	1/3/0	1/3/0	1/3/0	1/3/0	1/6/0	1/3/0
CHAR	E5	Electrical Characterization	Per Datasheet Parameters	-	1/30/0	1/30/0	1/30/0	1/30/0	-	-
CHAR	E5	Electrical Distributions	Cpk>1.67 Room, hot, and cold	-	-	-	-	-	3/90/0	3/90/0

QBS: Qual By Similarity, also known as Generic Data

Qual Device SN74HCS11PWR is qualified at MSL1 260C

Qual Device SN74HC14PWR is qualified at MSL1 260C

Qual Device SN74HCS14PWR is qualified at MSL1 260C

Qual Device SN74HCS4075PWR is qualified at MSL1 260C

Preconditioning was performed for Autoclave, Unbiased HAST, THB/Biased HAST, Temperature Cycle, Thermal Shock, and HTSL, as applicable

The following are equivalent HTOL options based on an activation energy of 0.7eV : 125C/1k Hours, 140C/480 Hours, 150C/300 Hours, and 155C/240 Hours

The following are equivalent HTSL options based on an activation energy of 0.7eV : 150C/1k Hours, and 170C/420 Hours

The following are equivalent Temp Cycle options per JESD47 : -55C/125C/700 Cycles and -65C/150C/500 Cycles

Quality and Environmental data is available at TI's external Web site: <http://www.ti.com/>

TI Qualification ID: R-CHG-2602-017

Group 2 Qualification Report

Approve Date 17-March-2026

Qualification Results

Data Displayed as: Number of lots / Total sample size / Total failed

Type	#	Test Name	Condition	Duration	Qual Device: SN74HC08DR	Qual Device: SN74HC14DR	Qual Device: SN74HCS14DR	Qual Device: SN74HCS266DR	QBS Process Reference: SN74HCS74QPWRQ1	QBS Package Reference: SN74LVC11ADRQ1	QBS Package Reference: SN74LVC132ADRQ1	QBS Package Reference: SN74LVC74ADRQ1	QBS Product Reference: SN74HC05DR	QBS Product Reference: SN74HC08PWR	QBS Product Reference: SN74HC14PWR	QBS Product Reference: SN74HCS14PWR
HAST	A2	Biased HAST	130C/85%RH	96 Hours	-	-	-	-	3/231/0	1/77/0	1/77/0	1/77/0	-	-	-	-
UHAST	A3	Autoclave	121C/15psig	96 Hours	-	-	-	-	3/231/0	1/77/0	1/77/0	1/77/0	-	-	-	-
TC	A4	Temperature Cycle	-65C/150C	500 Cycles	-	-	-	-	3/231/0	1/77/0	1/77/0	1/77/0	-	-	-	-
HTSL	A6	High Temperature Storage Life	150C	1000 Hours	-	-	-	-	3/135/0	-	-	-	-	-	-	-
HTSL	A6	High Temperature Storage Life	175C	500 Hours	-	-	-	-	-	1/45/0	1/45/0	1/45/0	-	-	-	-
HTOL	B1	Life Test	125C	1000 Hours	-	-	-	-	3/231/0	-	-	-	-	-	-	-
HTOL	B1	Life Test	150C	300 Hours	-	-	-	-	-	1/77/0	-	-	-	-	-	-
ELFR	B2	Early Life Failure Rate	125C	48 Hours	-	-	-	-	3/2400/0	-	-	-	-	-	-	-
SD	C3	PB Solderability	Precondition w.155C Dry Bake (4 hrs +/- 15 minutes)	-	-	-	-	-	1/15/0	-	-	-	-	-	-	-
SD	C3	PB-Free Solderability	Precondition w.155C Dry Bake (4 hrs +/- 15 minutes)	-	-	-	-	-	1/15/0	1/15/0	-	-	-	-	-	-
PD	C4	Physical Dimensions	Cpk>1.67	-	-	-	-	-	3/30/0	1/10/0	1/10/0	1/10/0	-	-	-	-
ESD	E2	ESD CDM	-	250 Volts	1/3/0	1/3/0	1/3/0	1/3/0	-	-	-	-	-	1/3/0	1/3/0	1/3/0
ESD	E2	ESD CDM	-	500 Volts	-	-	-	-	1/3/0	1/3/0	1/3/0	1/3/0	-	-	-	-
ESD	E2	ESD HBM	-	1000 Volts	-	-	-	1/3/0	-	-	-	-	-	1/3/0	1/3/0	1/3/0
ESD	E2	ESD HBM	-	2000 Volts	-	-	-	-	1/3/0	1/3/0	-	-	-	-	-	-
LU	E4	Latch-Up	Per JESD78	-	-	-	-	1/3/0	1/6/0	1/3/0	-	-	-	1/3/0	1/3/0	1/3/0
CHAR	E5	Electrical Characterization	Per Datasheet Parameters	-	1/30/0	1/30/0	1/30/0	1/30/0	-	-	-	-	1/30	1/30/0	1/30/0	1/30/0
CHAR	E5	Electrical Distributions	Cpk>1.67 Room, hot, and cold	-	-	-	-	-	3/30/0	2/60/0	1/30/0	1/30/0	-	-	-	-

QBS: Qual By Similarity, also known as Generic Data

Qual Device SN74HC08DR is qualified at MSL1 260C

Qual Device SN74HC14DR is qualified at MSL1 260C

Qual Device SN74HCS14DR is qualified at MSL1 260C

Qual Device SN74HCS266DR is qualified at MSL1 260C

Preconditioning was performed for Autoclave, Unbiased HAST, THB/Biased HAST, Temperature Cycle, Thermal Shock, and HTSL, as applicable

The following are equivalent HTOL options based on an activation energy of 0.7eV : 125C/1k Hours, 140C/480 Hours, 150C/300 Hours, and 155C/240 Hours

The following are equivalent HTSL options based on an activation energy of 0.7eV : 150C/1k Hours, and 170C/420 Hours

The following are equivalent Temp Cycle options per JESD47 : -55C/125C/700 Cycles and -65C/150C/500 Cycles

Quality and Environmental data is available at TI's external Web site: <http://www.ti.com/>

TI Qualification ID: R-CHG-2601-070

Qualification Report

Approve Date 17-March-2026

Qualification Results

Data Displayed as: Number of lots / Total sample size / Total failed

Type	#	Test Name	Condition	Duration	Qual Device: SN74HC05DR	Qual Device: SN74HC10DR	QBS Process Reference: SN74HCS74QFWRQ1	QBS Package Reference: SN74LVC11ADRQ1	QBS Package Reference: SN74LVC132ADRQ1	QBS Package Reference: SN74LVC74ADRQ1	QBS Product Reference: SN74HCS14PWR
HAST	A2	Biased HAST	130C/85%RH	192 Hours	-	-	3/231/0	1/77/0	1/77/0	1/77/0	-
HAST	A2	Biased HAST	130C/85%RH	96 Hours	-	-	3/231/0	1/77/0	1/77/0	1/77/0	-
UHAST	A3	Autoclave	121C/15psig	96 Hours	-	-	3/231/0	1/77/0	1/77/0	1/77/0	-
TC	A4	Temperature Cycle	-65C/150C	500 Cycles	-	-	3/231/0	1/77/0	1/77/0	1/77/0	-
HTSL	A6	High Temperature Storage Life	150C	1000 Hours	-	-	3/135/0	-	-	-	-
HTSL	A6	High Temperature Storage Life	175C	500 Hours	-	-	-	1/45/0	1/45/0	1/45/0	-
HTOL	B1	Life Test	125C	1000 Hours	-	-	3/231/0	-	-	-	-
HTOL	B1	Life Test	150C	300 Hours	-	-	-	1/77/0	-	-	-
ELFR	B2	Early Life Failure Rate	125C	48 Hours	-	-	3/2400/0	-	-	-	-
SD	C3	PB Solderability	Precondition w.155C Dry Bake (4 hrs +/- 15 minutes)	-	-	-	1/15/0	-	-	-	-
SD	C3	PB-Free Solderability	Precondition w.155C Dry Bake (4 hrs +/- 15 minutes)	-	1/22/0	-	1/15/0	1/15/0	-	-	-
PD	C4	Physical Dimensions	Cpk>1.67	-	-	-	3/30/0	1/10/0	1/10/0	1/10/0	-
ESD	E2	ESD CDM	-	250 Volts	1/3/0	1/3/0	-	-	-	-	1/3/0
ESD	E2	ESD CDM	-	500 Volts	-	-	1/3/0	1/3/0	1/3/0	1/3/0	-
ESD	E2	ESD HBM	-	1000 Volts	-	1/3/0	-	-	-	-	1/3/0
ESD	E2	ESD HBM	-	2000 Volts	-	-	1/3/0	1/3/0	-	-	-
LU	E4	Latch-Up	Per JESD78	-	-	1/3/0	1/6/0	1/3/0	-	-	1/3/0
CHAR	E5	Electrical Characterization	Per Datasheet Parameters	-	1/30/0	1/30/0	-	-	-	-	1/30/0
CHAR	E5	Electrical Distributions	Cpk>1.67 Room, hot, and cold	-	-	-	3/90/0	2/60/0	1/30/0	1/30/0	-

QBS: Qual By Similarity, also known as Generic Data

Qual Device SN74HC05DR is qualified at MSL1 260C

Qual Device SN74HC10DR is qualified at MSL1 260C

Preconditioning was performed for Autoclave, Unbiased HAST, THB/Biased HAST, Temperature Cycle, Thermal Shock, and HTSL, as applicable

The following are equivalent HTOL options based on an activation energy of 0.7eV : 125C/1k Hours, 140C/480 Hours, 150C/300 Hours, and 155C/240 Hours

The following are equivalent HTSL options based on an activation energy of 0.7eV : 150C/1k Hours, and 170C/420 Hours

The following are equivalent Temp Cycle options per JESD47 : -55C/125C/700 Cycles and -65C/150C/500 Cycles

Quality and Environmental data is available at TI's external Web site: <http://www.ti.com/>

TI Qualification ID: R-CHG-2602-006

In performing change qualifications, Texas Instruments follows integrated circuit industry standards in performing defect mechanism analysis and failure mechanism-based accelerated environmental testing to ensure wafer fab process, assembly process and product quality and reliability. As encouraged by these standards, TI uses both product-specific and generic (family) data in qualifying its changes. For devices to be categorized as a 'product qualification family' for generic data purposes, they must share similar product, wafer fab process and assembly process elements. The applicability of generic data (also known at TI as Qualification by Similarity (QBS)) is determined by the Reliability Engineering function following these industry standards. Generic data is shown in the qualification report in columns titled "QBS Process" (for wafer fab process), "QBS Package" (for assembly process) and "QBS Product" (for product family).

For questions regarding this notice, e-mails can be sent to the Change Management team or your local Field Sales Representative.

IMPORTANT NOTICE AND DISCLAIMER

TI PROVIDES TECHNICAL AND RELIABILITY DATA (INCLUDING DATASHEETS), DESIGN RESOURCES (INCLUDING REFERENCE DESIGNS), APPLICATION OR OTHER DESIGN ADVICE, WEB TOOLS, SAFETY INFORMATION, AND OTHER RESOURCES “AS IS” AND WITH ALL FAULTS, AND DISCLAIMS ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR NON-INFRINGEMENT OF THIRD PARTY INTELLECTUAL PROPERTY RIGHTS.

These resources are intended for skilled developers designing with TI products. You are solely responsible for (1) selecting the appropriate TI products for your application, (2) designing, validating and testing your application, and (3) ensuring your application meets applicable standards, and any other safety, security, or other requirements. These resources are subject to change without notice. TI grants you permission to use these resources only for development of an application that uses the TI products described in the resource. Other reproduction and display of these resources is prohibited. No license is granted to any other TI intellectual property right or to any third party intellectual property right. TI disclaims responsibility for, and you will fully indemnify TI and its representatives against, any claims, damages, costs, losses, and liabilities arising out of your use of these resources.

TI’s products are provided subject to TI’s Terms of Sale (www.ti.com/legal/termsofsale.html) or other applicable terms available either on ti.com or provided in conjunction with such TI products. TI’s provision of these resources does not expand or otherwise alter TI’s applicable warranties or warranty disclaimers for TI products.